



SIAM ENGINEERING CERAMICS CO., LTD.

204/6 Village No7, T.Charoen Tham, A.Wihan Daeng, Saraburi, 18150

Tel : +66-3634-0414 Fax : +66-3634-0242 E-mail : sec@secrefrac.com

CAST-15

SEC-Spec-CAST-15 Rev.00

TECHNICAL DATA SHEET

CAST-15 is a high alumina castable, consisting of purity bauxite, resist abrasion, acid slag and thermal spalling. Extra strength and high density castable which exhibits volume stability. It's recommended for uses in conditions which require load bearing strength and thermal spalling resistance in high temperature. It's a fast setting castable which suits rapid working. In applications such as sidewalls and roofs of boiler furnace and metal melting furnaces.

PHYSICAL PROPERTIES :

Maximum Service Temperature	°C	1580
Maximum Grain Size of Aggregates	mm	5.0
Approximate Weight Required for Casting	kg/m ³	2220
Approximate Amount of Water Required for Casting	%	12
Bulk Density After Drying at 110°C	kg/m ³	2280
Cold Crushing Strength after Drying at 110°C	kg/cm ²	300-400
Cold Crushing Strength after Heating at 1480°C	kg/cm ²	700
Permanent Linear Change After Heating at 1480°C	%	-0.2

CHEMICAL ANALYSIS :

Alumina (Al ₂ O ₃)	%	58.2
Silica (SiO ₂)	%	36.0
Iron Oxide (Fe ₂ O ₃)	%	1.0

THERMAL CONDUCTIVITY :

	Kcal/ hr.m.°C
at 400 °C	0.93
at 600 °C	0.95
at 1000 °C	0.98

The above data are typical properties for the most commonly produced commercial sizes. All data subject to reasonable deviation only, and should not be used for specification purposes. ASTM test methods, and SEC's written procedure, where applicable used for determination of data.

"Quality and Services are Our Mission"

SP-RD-02, Rev.02, 29/05/67